












Trevor Selby
 Phone +44(0) 1425 473700
 Email. trevor@aافت.com.au
 8 Hampton Drive
 Ringwood Hampshire UK. BH24 1SL

OFDA 2000 REPORT : SORTED BY MICRON
 Samples 04/07/2013 (11Records)

Job Details
 Bamby Alpaca Farm
 Reference: 0194 - 0194
 Tested: Jul 04, 2013

Animal Eartag	Mic Ave	SD Mic	CV Mic	CEM	<15 %	CF %	SL mm	Min Mic	Max Mic	Fibre Ends	SD Along	CRV Dg/mm	Lot Dest
Averages	21.2	4.3	20.2	8.7	5.4	94.8	105.5	19.6	23.2		0.99	39.0	
 BAM Fallon	17.4	3.5	19.9	7.1	18.2	100.0	125.0	16.5	19.0	-0.2	0.70	38.7	Ultrafine
 BAM Fantasy	18.2	3.8	20.9	7.4	15.6	99.5	125.0	16.1	20.6	-0.6	1.20	39.8	Superfine
 BAM Flavius	18.8	3.7	19.4	8.0	7.5	99.3	95.0	17.3	20.3	-1.3	1.00	37.5	Superfine
 BAM Freya	19.5	4.2	21.5	8.4	9.1	98.2	135.0	18.2	22.4	-0.9	1.20	40.2	Superfine
 CL07 Adonia	20.8	4.3	20.6	9.3	1.6	95.9	80.0	19.9	22.4	-0.3	0.80	41.2	Fine
 BAM Desteny	21.2	5.1	24.0	10.7	4.7	93.7	100.0	19.6	23.9	-0.6	1.00	43.2	Fine
 BAM Echo	21.3	3.8	18.0	7.6	1.7	97.6	115.0	19.5	23.8	0.2	1.00	42.0	Fine
 BAM Bamby	22.2	4.5	20.2	9.4	0.7	94.1	70.0	21.4	23.7	0	0.80	40.6	Fine
 BAM Chibar	22.7	4.0	17.7	7.9	0.2	95.6	90.0	20.7	23.7	-1.5	0.80	36.8	Fine
 BAM Dreamdancer	25.2	5.1	20.4	9.8	0.4	85.4	135.0	22.4	26.7	-0.9	1.10	29.2	Medium
 BAM Calou	25.6	5.0	19.6	9.7	0.1	83.7	90.0	23.8	29.2	-0.9	1.30	40.3	Medium